

TEST REPORT

No. 4116214/1 dated 10th July 2014

PU Sealer satin



Type of testing:

Determination of surface properties of sports surfaces being treated with maintenance products or coatings in accordance with DIN V 18032 Part 2:2001-04, - Sports floors and DIN EN 14904:2006

Applicant:

CC- Dr. Schutz GmbH
Steinbrinksweg 30
31840 Hessisch Oldendorf
GERMANY

Contact Person: Mr. Dr. D. Reindl

Tel: +49 (0) 5152 977916
Fax: +49 (0) 5152 922926

d.reindl@eukula.com
www.dr-schutz.com

Test Institute:

ISP – Institut für Sportstättenprüfung
Dr. Uwe Schattke
Stormweg 6
49196 Bad Laer
Germany

Contact Person: Mr. D. Frank

Tel: +49 (0) 5424 / 80 97 891
Fax: +49 (0) 5424 / 80 97 893

D.Frank@ISP-Germany.com
www.ISP-Germany.com

ISP-Ref.-no.:

4116214

The Institut für Sportstättenprüfung is an DIN EN ISO / IEC 17025:2005 accredited testing laboratory, by the German accreditation body DAkkS GmbH. The accreditation covers the test methods listed in the accreditation certificate.

Assessments and interpretations are not subject to the accreditation.

The test report includes 4 pages. Reproduction and publication of this document in shortened text and the use of advertising is permitted only with the written approval of the ISP.

The test results relate only to the tested measurement points.

Manufacturer: see applicant

Test location: **ISP – Institut für Sportstättenprüfung**
Laboratorium
Südstr. 1a
49196 Bad Laer
Germany

Date of testing: 16.09. – 08.10.2013

Technician: P. Dück and D. Frank

ISP Sample-no.: 2120913/3

Author of this report: J. Sliwinski

1. Sample Description

According to the applicant the sample is declared as followed:

2120913/3	PVC flooring glued on an OSB with the client's declaration: "Belag vergütet, PU Siegel Matt" dimensions: 50 x 50 cm Product name: PU Sealer satin
-----------	--

The sample has been received in the ISP laboratory on the 06th June 2013.

2. Test Procedure

The sample has been tested according to the following parameters:

Determination of friction (DIN V 18032-2:2001-04)
Determination of friction (DIN EN 14904:2006)

The friction in accordance with DIN V 18032-2:2001-04 had been determined at an ISO 17025 accredited third party test institute and is therefore not covered with the ISO 17025 accreditation of the ISP. The test results have been implemented into this report. The original report is stored in the ISP archive.

3. Test Results

3.1 Test results in accordance with DIN V 18032-2:2001-04

Sample	Unit	Results					Requirement
2120913/3							
I Average	- -	0.57	0.55	0.54 0.54	0.53	0.53	0.4 – 0.6
I = Individual value							

3.2 Test results in accordance with DIN EN 14904:2006

Sample	Unit	Results					Requirement
2120913/3							
D ₁ Average	- -	95	96	97 96	97	95	80 – 110
D ₂ Average	- -	99	102	103 101	100	100	80 – 110
D ₁ = Testing direction transversal D ₂ = Testing direction longitudinal							

4. Conclusions


The evaluation is based on the requirements of friction in accordance to DIN V 18032-2:2001 and DIN EN 14904:2006.

The PVC sample 2120913/3 PU Sealer satin fully meets the tested requirements.

END OF THE REPORT

This test report consists of 4 pages. Reproduction and publication of the document even in a short version are prohibited without our explicit permission.

Bad Laer, 10th July 2014



Dr. Uwe Schattke
MANAGING DIRECTOR



Dennis Frank
LABORATORY MANAGER