


PU Sealer



1 PRODUCT DESCRIPTION

Special water-based 2 part polyurethane permanent sealer for the long-term protection of floors. Only for professional users. Reduces dirt adhesion and the time needed for day-to-day maintenance.

- Hardwearing sealer film,
- excellent elasticity,
- good resistance against colorless chemicals,
- Easy and safe to apply with excellent adhesion.
- High solids content.
- UV Stable.
- Anti-slip classification R9.
- Tested according to DIN 18032-2 and DIN EN 14904, suitable for sports floors (satin).
- Very low emission (EMICODE: EC1 R).

Gloss grade at 60°:

- Gloss: 70-85
- Satin: 10-15
- Mat: 5-7

The gloss grade can vary from lab values depending on the conditions in actual buildings.

2 AREAS OF APPLICATION

- Floor coverings made of PVC and LVT with smooth, or slightly structured, grained surfaces.
- Linoleum floors, for open-pored linoleum after priming with **Dr. Schutz Lino Primer**.
- Non-absorbent stone and tile sub-surfaces after priming with **Dr. Schutz Superbond**.
- Epoxy and PU floors.
- Wood and cork floors after priming with **strato classic prime 200**.


Suitability for safety floorings, more structured surfaces and studded floors must be ascertained in the specific building before use (*).

Please pay attention to our technical recommendations specifically for floors and buildings under www.peerlessjal.com.au.

3 APPLICATION

Shake up **Dr. Schutz PU Sealer / Waxnomor** vigorously before adding the Crosslinker. Add **Crosslinker M** (for satin, mat), or **Crosslinker G** (for gloss) to the base lacquer in a ratio of 10:1 and immediately mix thoroughly and evenly. Allow the mixture to settle for 10 minutes, then stir again and use it. Do not mix more than can be used up within 4 hours (at 20 °C). Apply **PU Sealer / Waxnomor** evenly (at min. 15 °C) onto the previously prepared subsurface with the **Dr. Schutz Aquatop Roller** in two coats.

PU Sealer



Please note:

- The surface must be professionally prepared and in a clean, dry condition free of oil, wax and dust (**).
- Wood, open-pored linoleum and decorative screed floors must be primed before applying **Dr. Schutz PU Sealer / Waxnomor**.
- Floor and material temperature must not fall below +15°C during application and drying time.
- The technical rules are to be observed.

4 CONSUMPTION

Per coating approx. 20 m²/l (50 ml/m²). On wood, cork or decorative screed floors approx. 10-12m²/l (80-100 ml/m²) per coating.

In the case of a very absorbent sub-surface, higher consumption is possible, depending on absorbency.

5 DRYING TIME

Can be carefully walked on and worked on for the second coating after approx. 2 hours, but no longer than 12 hours after the first coat. In the case of a longer interim drying time, the entire surface must first be abraded with a **3M SPP Pad or Glomesh Floor Prep Pad (Single disc speed to be <150rpm)**. Can be walked on carefully 12 hours after the last sealing coat. After 24 hours approx. 80% of the durability has been achieved. After 7 days the full durability and chemical resistance of the product is provided (based on conditions of 20 °C, 50% relative humidity and sufficient ventilation)

Low temperatures, high humidity and poor ventilation can prolong the drying time. Refrain from laying down carpets in the first 10-14 days. Furniture can be carefully placed after 24 hours. The area must not be wet mopped in the first three days.

6 CLEANING & CARE


After the area has hardened completely, use **Peerless JAL Strobe or Versadet** for general cleaning.

In areas with high traffic, signs of wear, such as scratches or discoloration, may occur. This can mean that a renovation of parts or of the entire sealer surface is necessary, requiring the application of a new coat of **Dr. Schutz PU Sealer / Waxnomor**. We recommend that renovation of the sealer film is carried out on taped-off part areas.

In case conventional care is requested, we recommend **Peerless JAL Gemini Floor Polish** (Gloss or Satin).

Please pay attention to our care instructions specific to flooring and buildings at www.peerlessjal.com.au.

PU Sealer



7 STORAGE

Protect against frost. Store in a cool, dry place. Will keep for 12 months in unopened, original canister from the date of manufacture. Keep coating materials out of the reach of children.

When stored in varying temperatures and/or in an opened canister, dried parts can form. If so, sieve these out before using.

8 TECHNICAL DATA

Contained substances: water, polyacrylate, polyurethane, glycoether, silicic acids, waxes, additives. Contains 1,2-benzisothiazol-3(2H)-one. May produce an allergic reaction.

voc (g/l) 47 base (ISO11890) / 2004/42/IIA(j)(140)140.

ADR/RID: not a dangerous good as defined by transport regulations (base lacquer and crosslinker).

CLP (base lacquer): labelling not necessary.

Emptied canisters can be disposed of in household waste, or taken to a recycling centre.

CLP (Crosslinker G/M): GHS 07, Attention. H332 Harmful if inhaled. H317 May cause an allergic skin reaction. H335 May cause respiratory irritation. H412 Harmful to aquatic life with long lasting effects. P280 Wear protective gloves / eye protection. P362 Take off contaminated clothing. P405 Store locked up. EUH204 Contains isocyanates. May produce an allergic reaction.

9 SPECIAL NOTES


- When mixed together, 2part-products can develop carbon dioxide and build up pressure. Never close 2part-mixtures tightly in a container, danger of bursting!
- Clean the working tools and implements with water. The hardened remains of lacquer can only be removed mechanically. We recommend always using new, dry Aquatop Rollers.
- Please pay attention to the printed batch number. Only use products with the same batch number in one layer. In the case of a different batch, mix this in a separate container before using.
- Coloured products (e.g. hair dyes, coloured disinfectants for wounds) as well as plasticizer migration (e.g. from rubber) can lead to the irreversible discoloration of the sealing coat. If resistance to hand and instrument disinfectants is required in specific buildings, we recommend pre-testing the respective chemicals on site. (*)
- (*) In case of questions, please consult our advice on technical applications
- (**) Please pay attention to our Technical Information "Preparation of subsurfaces"

10 CROSS-REFERENCE

Our following publications in their updated form are valid as an integral part of this fact sheet:

- General notes on the application of Dr. Schutz finishes
- Safety data sheet.

PU Sealer



The quoted printed matter, as well as this product information in its updated form, is available on our homepage www.peerlessjal.com.au or on request from the address quoted below.

eukula – We Care About Wood Floors

Peerless JAL
Head Office
6-12 Raglan St, Preston
VIC, 3072

Ph: 1800 800 248
Fax: 03 9416 8516
Email: sales@peerlessjal.com.au
www.peerlessjal.com.au

The above advice for technical application is given to the best of our knowledge and according to the latest state of technology. Therefore, if our products are used carefully heeding the advice given on their application, as well as following our suggested procedures with the materials intended for use with these products, no damage shall occur. However, our products are used outside and beyond our possible control, and are therefore subject to your own responsibility, which does not release you from the obligation to check for yourself whether our supplied products are suitable for your intended purpose and procedure. Therefore our notes and advice are not legally binding and cannot be used against us as grounds for liability - which includes the rights and protection of any third party. The relevant recommendations, guidelines and standard norms are to be observed, as well as the recognized technical rules. On publication, this product information replaces and supersedes the validity of any previous versions.